



MONDÉCO

Seamless terrazzo flooring that delivers a stylish surface suited for use in upmarket commercial environments

www.flowcreteasia.com

Mondéco Seamless Terrazzo Technical Profile



Flowcrete's seamless terrazzo flooring range, Mondéco, is the ultimate surface material for commercial environments owing to its eye-catching and durable finish.

Terrazzo flooring dates back to Ancient Rome where its vibrant, wear-resistant and flexible qualities proved popular with forwardthinking architects building the first modern empire.

Fast-forward to the present day, where Flowcrete's take on this impressive flooring solution remains the first-choice for designers across the globe. Offering a mix of aggregates ranging from sparkling crystal mirror glass right through to tough flint and granite chippings, the Mondéco range is the designer's dream for all interior flooring projects.

Application Suitability



Retail



Transport



Leisure



Offices




Airports



Pharmaceutical

Creative Design Potential

Mondéco can be installed in a variety of complicated patterns using brass or aluminium trims, which are laid on the surface of the floor in a matrix that designates each area of the design. Mondéco is simply used to fill each colour block before the whole surface is ground to reveal the stunning design.



Technical Profile

FIR RESISTANCE


| EN 13501-1 | B _{FL} - s1 | |
|---|--|--|
| SLIP RESISTANCE | | |
| Method described in BS 7976-2 (typical values for 4-S rubber slider) | Dry >40, Wet depends on specification (in accordance with HSE and UKSRG guidelines) | |
| TEMPERATURE RESISTANCE | | |
| Tolerant of sustained temperatures up to 60°C | | |
| WATER PERMEABILITY | | |
| Karsten Test | Nil (Impermeable) | |
| ABRASION RESISTANCE | | |
| BS 8204-2 | Grade AR2 | |
| COMPRESSIVE STRENGTH | | |
| EN 13892-2 | >55 N/mm² | |
| FLEXURAL STRENGTH | | |
| EN 13892-2 | >20 N/mm ² | |
| | | |

 $> 10 \text{ N/mm}^2$

Mondéco Crystal (6 mm)

A seamless, highly decorative, solvent free, epoxy resin terrazzo floor finish incorporating recycled, clear crystal glass aggregates.

Mondéco Crystal is suitable for airport terminals, shopping centres, hotels, and environments where design and aesthetics are key.



178-1

Durable for a long lifecycle

Resistant to chemials and traffic

000000

Ûn.



TENSILE STRENGTH

BS 6319





Aquamarine



Ebony





Yellow



Grey



For applications falling outside of this temperature range, please contact your local Flowcrete Technical Department. ** Cure times at temperatures between 0-30°C can be achieved by altering the quantity of catalyst used.

Mondéco Splash (6 mm)

A seamless, highly decorative, solvent free, epoxy resin terrazzo floor finish incorporating recycled clear and coloured glass aggregates.

Mondéco Splash is suitable for environments where design and durability are key, such as airport and railway terminals, shopping centres, hotels and restaurants.



Attractive:

Offers extensive design potential to deliver the wow-factor underfoot.



Easy to Clean:

Delivers a hygienic seam-free surface that is easy to clean and maintain.



Durable:

A highly durable finish that delivers an impressive lifecyle.



Chemical Resistant:

Provides protection against chemicals and corrosive cleaning agents.



Resistant:

Holds its own against impact and sustained foot and wheeled traffic.

Standard Colours







Amber Stone

Cherry Opal


1

Emerald

Yellow Sapphire

Technical Profile

| FIRE RESISTANCE | | | | | |
|---|--|----------|-------------------|--|--|
| EN 13501-1 | B _{FL} - s1 | | | | |
| SLIP RESISTANCE | SLIP RESISTANCE | | | | |
| Method described in BS 7976-2 (typical values for 4-S rubber slider) | Dry >40, Wet depends on specification (in accordance with HSE and UKSRG guidelines) | | | | |
| TEMPERATURE RESISTANC | E | | | | |
| Tolerant of sustained tempero | atures up t | o 60°C | | | |
| WATER PERMEABILITY | WATER PERMEABILITY | | | | |
| Karsten Test | Nil (Impermeable) | | | | |
| ABRASION RESISTANCE | | | | | |
| Grade AR2 - Medium duty In | dustrial ar | nd Comme | ercial | | |
| COMPRESSIVE STRENGTH | | | | | |
| EN 13892-2 | >55 N/r | nm² | | | |
| FLEXURAL STRENGTH | | | | | |
| EN 13892-2 | >20 N/mm ² | | | | |
| TENSILE STRENGTH | | | | | |
| BS 6319 | >10 N/mm ² | | | | |
| BOND STRENGTH | | | | | |
| >1.5 MPa* | | | | | |
| SPEED OF CURE** | 10°C | 20°C | 30°C | | |
| Light Traffic | 24 hrs | 20 hrs | 16 hrs | | |
| Full Traffic | 72 hrs | 48 hrs | 36 hrs | | |
| Full Chemical Cure | 12 days | 7 days | 6 days | | |
| Mondéco Mondéco Splash Grout | Thixogr | | Mondéco Sealer | | |



*Assumes concrete compressive strength is greater than 25N/mm²

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

Application Suitability

1

1

| Food & drink | |
|---------------------|---|
| Pharmaceutical | ~ |
| Engineering | |
| Offices | ~ |
| Chemical processing | |
| Manufacturing | |
| Retail environments | ~ |
| Transport | ~ |
| Stadia | ~ |
| Education | ~ |
| Airports | ~ |
| Healthcare | ~ |

THESCHOOL

L.L.

L.

J.L

For applications falling outside of this temperature range, please contact your local Flowcrete Technical Department ** Cure times at temperatures between 0-30°C can be achieved by altering the quantity of catalyst used.

Mondéco Earth (6 mm)

A seamless, highly decorative, solvent free, epoxy resin terrazzo floor finish incorporating granite and flint aggregates.

Mondéco Earth is aesthetically pleasing whilst also being suitable for environments where hygiene, chemical resistance and durability are key, such as pharmaceutical production and process areas.



Attractive:

Offers extensive design potential to deliver the wow-factor underfoot.



Easy to Clean:

Delivers a hygienic seam-free surface that is easy to clean and maintain.



Durable:

A highly durable finish that delivers an impressive lifecyle.



Chemical Resistant:

Provides protection against chemicals and corrosive cleaning agents.



Resistant:

Holds its own against impact and sustained foot and wheeled traffic.

Standard Colours





Chilli Peppe

Peach

Almond



Coconut





Pomegranate


Tangerine

Blueberr

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

Technical Profile

| FIRE RESISTANCE | | | | |
|---|--|--------|--------------------|--|
| EN 13501-1 | B _{FL} - s1 | | | |
| SLIP RESISTANCE | | | | |
| Method described in BS 7976-2 (typical values for 4-S rubber slider) | Dry >40, Wet depends on specification (in accordance with HSE and UKSRG guidelines) | | | |
| TEMPERATURE RESISTANC | E | | | |
| Tolerant of sustained temperatures up to 60°C | | | | |
| WATER PERMEABILITY | | | | |
| Karsten Test | Nil (Impermeable) | | | |
| ABRASION RESISTANCE | | | | |
| Taber Abrader | 50 mg loss per 1000 cycles (1 kg load using CS17 wheels) | | | |
| COMPRESSIVE STRENGTH | | | | |
| EN 13892-2 | >55 N/mm² | | | |
| FLEXURAL STRENGTH | | | | |
| EN 13892-2 | >20 N/mm ² | | | |
| TENSILE STRENGTH | | | | |
| BS 6319 | >10 N/mm ² | | | |
| BOND STRENGTH | | | | |
| > 1.5 MPa* | | | | |
| SPEED OF CURE** | 10°C | 20°C | 30°C | |
| Light Traffic | 24 hrs | 20 hrs | 16 hrs | |
| Full Traffic | 72 hrs | 48 hrs | 36 hrs | |
| Full Chemical Cure | 12 days | 7 days | 6 days | |
| Mondéco Mondéco Earth Grout | Thixogr | | owseal UV Clear | |



*Assumes concrete compressive strength is greater than 25N/mm²



1F

Application Suitability

| Food & drink | |
|---------------------|---|
| Pharmaceutical | ✓ |
| Engineering | |
| Offices | ✓ |
| Chemical processing | |
| Manufacturing | |
| Retail environments | ✓ |
| Transport | ✓ |
| Stadia | ✓ |
| Education | ✓ |
| Airports | ✓ |
| Healthcare | ~ |





www.flowcreteasia.com



asia@flowcrete.com