



## Flowfresh SL (2mm)

A pigmented, antimicrobial, self-smoothing, polyurethane resin floor finish applied at a thickness of approximately 2mm.

Provides a hygienic floor finish for dry or semi-wet F&B processing areas.



### Hygienic:

Contains Polygiene®, an antimicrobial additive that inhibits bacteria growth.



### HACCP International Certified:

Certified as food-safe for use in wet and dry food handling areas.



### High Chemical Resistance:

Protects against a majority of acids used in manufacturing processes.



### Abrasion Resistant:

A hard-wearing & abrasion resistant finish to protect the substrate below.



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

## Technical Profile\*

FIRE RESISTANCE				
EN 13501-1	B <sub>n</sub> - s1			
SLIP RESISTANCE**				
Method described in BS 7976-2 (typical values for 4-S rubber slider)	Dry >40, Wet depends on specification (in accordance with HSE and UKSRG guidelines)			
IMPACT RESISTANCE				
BS8204 Part 1 Cat: A (<0.5mm) ISO6272	1kg weight > 1.8m 2kg weight > 1.5m			
WATER PERMEABILITY				
Nil – Karsten test (impermeable)				
TEMPERATURE RESISTANCE				
From 5°C to 65°C				
CHEMICAL RESISTANCE				
Contact Technical Department Excellent resistance to sugars and most acids				
ABRASION RESISTANCE				
Taber Abrader (1 kg load using CS17 wheels)	0.1g loss per 1000 cycles			
COMPRESSIVE STRENGTH				
EN 13892-2	>50 N/mm <sup>2</sup>			
FLEXURAL STRENGTH				
EN 13892-2	>20 N/mm <sup>2</sup>			
TENSILE STRENGTH				
BS 6319	>10 N/mm <sup>2</sup>			
COEFFICIENT OF THERMAL EXPANSION				
ASTM C531	5.70 x 10 <sup>-5</sup> °C <sup>-1</sup>			
BOND STRENGTH				
Greater than cohesive strength of 25 N/mm <sup>2</sup> concrete. >1.5 MPa				
SPEED OF CURE		10 °C	20 °C	30 °C
Light Traffic		36 h	24 h	12 h
Full Traffic		72 h	48 h	24 h
Full Chemical Cure		10 d	7 d	6 d


\* These figures are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity. \*\*The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.

## Model Specification

<b>System</b>	Flowfresh SL
<b>Finish</b>	Matt
<b>Thickness</b>	2mm
<b>Manufacturer</b>	Flowcrete Asia

Preparatory work and application in accordance with manufacturer's instructions.

## System Design



## Products Included In This System

<b>Primer</b>	Flowfresh Primer
<b>Finishing Coat</b>	Flowfresh SL

Detailed application instructions are available upon request.

## Available in Multi-Pack Supply Format

- Flowfresh HF/MF/RT (A+B)
- Flowfresh SL Filler C Blank
- Flowfresh Pigment Paste

## Substrate Requirements

Concrete/screed substrate should be a minimum of 25N/mm<sup>2</sup>, free from laitance, dust and other contamination. Substrate should be surface dry and free from rising damp and ground water pressure.

## Installation Service

The installation should be carried out by a licensed contractor with a documented quality assurance scheme. For details of our licensed contractors, contact our customer service team or enquire via our website at [www.flowcreteasia.com](http://www.flowcreteasia.com)

## Microbial / Fungal Resistance

The Polygiene® antimicrobial additive incorporated into Flowfresh SL provides control of most bacteria and fungi which come into contact with the floor.

## Environmental Considerations

The system is assessed as non-hazardous to health & the environment. The long service life & seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

## HACCP International Certification

Flowfresh has been evaluated to international standards and a set of key food safety criteria for potential physical, chemical and microbiological food safety risks by a team of degree qualified food technologists and product assessors. The Flowfresh range has been identified as food-safe for use in wet and dry food handling areas such as kitchens, production areas and processing areas operating a HACCP based Food Safety Program, noting the conditions of the certification statement SSZ. HACCP International operates a world renowned product certification scheme for equipment, materials and services used within the global food and beverage processing, production and packaging sector - confirming a product's suitability for use within food businesses that operate to the world's highest standards.

## Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

## Important Note

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages.

## Further Information

To ensure you are specifying a fit-for-purpose floor, please consult our Technical Advisors or visit our website to register your interest in specifying one of the most durable floors on the market.

1. Light colours may require additional coats to achieve desired results 2. It is recommended that top coat colours are close to base coats colours to achieve desired results  
3. This product is not UV stable and may discolour unless otherwise stated 4. System Data Sheet to be read in conjunction with Method Statement and Product data Sheets.