DEHYDRATINE 75



EMULSIFIED ASPHALT DAMPPROOFING COMPOUND

DESCRIPTION

DEHYDRATINE 75 is a VOC compliant, water-based compound designed to dampproof concrete and masonry. The **DEHYDRATINE** formulation is derived from colloidal, asphalt-based clay emulsions, that utilise a water carrier. It can be used above and below grade. **DEHYDRATINE 75** is highly effective and is easily applied by trowel or spray.

FEATURES / BENEFITS

DEHYDRATINE 75 is an effective dampproofing product on roofing materials such as fibre glass fabric and metal (see Roofing under Application Techniques). **DEHYDRATINE 75** can be used over most metals to protect against rust and corrosion. It has good weathering and abrasion resistance. It resists flow or sag even when exposed to high ambient temperatures. Other advantages include:

- · Solvent free
- Adheres tenaciously to damp or "green" surfaces
- · Breathes to allow water vapour to escape and reduce blistering
- · Flexible and will not crack as a result of normal contraction & expansion
- Asbestos free

SPECIFICATIONS/COMPLIANCES

ASTM D 1227 Type III ASTM D 1187 Type I

Appearance: **DEHYDRATINE 75** is black.

PACKAGING

DEHYDRATINE 75 is packaged in 20 kg and 200 kg containers.

SHELF LIFE

1 year in original, unopened package

COVERAGE

One Coat Application	m^2/L
(Not more than)	1.33
Two Coat Application	
1st coat	1.33

 1st coat
 1.33

 2nd coat
 1.33

Coverage rates are approximate and for estimating purposes only. Surface temperature, porosity and texture will determine actual material requirements.

DIRECTIONS FOR USE

Surface Preparation: Surface must be structurally sound, clean, free of dust, dirt, mortar, residue curing and parting compounds, and other contaminants. Use of wire brushes, sandblasting or other mechanical means is recommended. Prior to application, surface defects, voids, joints or cracks must be properly

sealed or filled. Dry surfaces should be dampened with water and kept damp before application.

Mixing: Stir DEHYDRATINE 75 well before use.

Application: Apply by soft bristle brush or suitable spray equipment at a rate of not more than 1.33 m²/L in a single coat. When two coats are applied in hot weather when it may be difficult to keep the surface damp, the first coat may be diluted with up to 10% of clean, cool water. The first coat should be dry to the point where it is tacky to the touch before the second coat is applied.

Backfilling: Do not backfill until the film has dried (at least 24 to 48 hours after application). Backfilling should be accomplished as soon as possible (after 24 to 48 hours) to protect the film from damage by outside sources. Place backfill with care so that the film will not be ruptured.

Roofing: DEHYDRATINE 75 can be used with fibreglass fabric for built-up waterproofing and roofing applications. **DEHYDRATINE 75** has excellent rust inhibiting qualities and can be applied as a coating over metal roofs. It has good weathering properties and resistance to corrosive fumes and smoke.

CLEAN UP

Clean tools or equipment with mineral spirits immediately following use. Clean drips while still wet. **DEHYDRATINE 75** will not harm glass or metal by etching, pitting, or staining; however, it will leave a residue which is easily removed with a clean cloth and petroleum based paint thinner. Stronger solvents may be required to remove the residue if allowed to remain on the surface. Once final set has occurred, **DEHYDRATINE 75** may be impossible to remove from surfaces. Flush rubber surfaces with water immediately following contact with **DEHYDRATINE 75**.

PRECAUTIONS / LIMITATIONS

- Do not apply DEHYDRATINE 75 to surfaces that will receive a concrete overlay or topping, or will be sealed with another type of sealer.
- Mask or protect the sides of joints prior to the application of DEHYDRATINE 75.
- Applications of **DEHYDRATINE 75** at coverage rates greater than those recommended above may result in improper drying.
- Do not allow to freeze.
- In all cases, consult the Safety Data Sheet before use.

Rev: 13/10/16